



## Gecko® Bond Star

Solvent based printing inks for flexible packaging  
Universal lamination



### Description

A full colour range of highly pigmented nitrocellulose printing inks designed for reverse printed lamination applications on flexible films, supplied as finished products or for use as mono component concentrates and additives within an ink dispenser formulation.

### Applications

Flexible packaging for food and beverage products printed on chemically treated polyester, polypropylene and polyamide films. Lamination bond are dependent on substrate type and quality, adhesive type and film weight applied.

### Print Process

Reverse print Flexographic and Rotogravure for lamination.

### Properties

Ink adhesion	see additives	Water resistance	n/a
Rub resistance	n/a	Deep freeze resistance	n/a
Anti-scratch	n/a	Vegetable oil resistance	n/a
Heat resistance	n/a	C.O.F. (dynamic)	n/a
Gloss	n/a	Light fastness (BWS)	3-7
Lamination bond	> 2.0 N/15 mm	Lamination heat seal bond	> 2.0 N/15 mm

**Rating scale** (1 to 5 based on Gecko product range) 1 = worst value, 5 = best value

**Note:** All technical properties are a guideline only and dependant on pigment choice and final application

Substrates: Coex OPP, ChemPET, BOPA, coronaPET\*

Secondary Web: Coex OPP, PE, ChemPET

\* for applications on corona treated PET, under any circumstances lamination performance must be tested prior to production. The use of Xtreme White 77GW289635 is highly recommended for applications including coronaPET.

## Print viscosity

Diluents	Flexographic	Gravure
	20 - 25 sec. DIN 4	15 - 20 sec. DIN 4
Slow	N. Propanol/N. Propyl Acetate 9:1	N. Propanol/N. Propyl Acetate 3:1
Standard	Ethanol/Ethyl Acetate 9:1	Ethanol/Ethyl Acetate 3:1
Fast		Ethanol/Ethyl Acetate
Retarder	Ethoxy Propanol	Ethoxy Propanol

## Auxiliaries

- White** Especially for applications on coronaPET the use of Xtreme White 77GW289635 is highly recommended.
- Metallics** A full range of Gecko® gold and silver inks is available.
- Additive** Gecko® Bond Star will not give immediate adhesion prior to lamination when printing directly on OPP. An adhesion promoter is available in order to improve initial adhesion.
- Process Inks** A range of slow drying flexo half-tone process colours are available.

## Instructions for the use of printing inks for the production of primary food packaging

For information on the use of printing inks for the manufacture of food packaging please refer to the respective „**Statement of Composition**“. This information is provided to allow the calculation of possible levels of migration of evaluated substances in a worst case situation.

Migration tests at **hubergroup** laboratories with printed samples made from commercially available OPP film (film thickness 35 µ, printed weight 6 g/m<sup>2</sup>, with ethanol as the food simulant) and PE film (50 µ, printed weight 6 g/m<sup>2</sup>, with ethanol as the food simulant) showed no migration of substances above legal limits. Based on the results of these migration tests, we expect that the printed inks enable the final printed products to comply with the legal requirements for packaging for all kinds of foodstuff.

The manufacturer of the finished article and the filler have the legal responsibility to prove by appropriate migration testing that it is fit for its intended purpose.

In order to maintain low residual solvents concentration in the printed film, the printer must ensure sufficient drying of the inks, especially when retarders have been added. Residual solvent content must be regularly monitored.

The inks must not be used in the manufacture of packaging where the printed ink layer is intended to come into contact with foodstuff (direct food contact).

There are restrictions for the use of printing inks for applications where temperatures above 120 °C for extended periods of time are applied. For details, please see document “Food Packaging Inks for High Temperature Applications”.

## Health & Safety

The material safety data sheets contain all relevant information for the generation of appropriate internal plant instructions. The user is responsible for all local legislation requirements.

## Ink Handling

Please refer to General Guidelines for handling inks for flexible packaging.

---

Contact addresses for advice and further information can be found under [www.hubergroup.de](http://www.hubergroup.de)

This Technical information sheet reflects the current state of our knowledge. It is designed to inform and advise. We assume no liability for correctness. Modifications may be made in the interest of technical improvement.