



Gecko® Zoom-PE

Solvent based printing inks for flexible packaging

Shrinkable packaging



Description

A full colour range of highly pigmented nitrocellulose printing inks designed for surface and reverse printing on polyethylene for shrink applications, supplied as finished products or for use as mono component concentrates and additives within an ink dispenser formulation.

Applications

Flexible packaging for shrink polyethylene multi-packs and sleeves for bottles and cans. Can also be used for standard surface printing applications on OPP.

Print Process

Surface print Flexographic and Rotogravure.

Properties

Ink adhesion	5	Water resistance	5
Rub resistance	4	Deep freeze resistance	5
Anti-scratch	4	Vegetable oil resistance	5
Heat resistance	limited by PE-film	C.O.F. (dynamic)	0.25 - 0.35
Gloss	4	Light fastness (BWS)	3 - 7

Rating scale (1 to 5 based on Gecko product range) 1 = worst value, 5 = best value

Note: All technical properties are a guideline only and dependant on final application

Substrates: PE, Coex OPP, Acrylic OPP

Print viscosity

Diluents	Flexographic 20-25 s DIN 4	Gravure 15-20 s DIN 4
Slow	N-Propanol/N-Propyl Acetate 9:1	N-Propanol/N-Propyl Acetate 3:1
Standard	Ethanol/Ethyl Acetate 9:1	Ethanol/Ethyl Acetate 3:1
Fast		Ethanol/Ethyl Acetate 1:1
Retarder	Ethoxy Propanol	Ethoxy Propanol

Auxiliaries

- Additives** Gecko® Zoom-PE will give very good adhesion when printing directly on PE-films. On OPP films addition of adhesion promoter (70GH278345) may be required.
- Process Inks** A range of slow drying flexo half-tone process colours are available.

Instructions for the use of printing inks for the production of primary food packaging

For information on the use of printing inks for the manufacture of food packaging please refer to the respective „**Statement of Composition**“. This information is provided to allow the calculation of possible levels of migration of evaluated substances in a worst case situation.

Migration tests at **hubergroup** laboratories with printed samples of the above mentioned product made from commercially available OPP film (film thickness 35 µ, printed weight 6 g/m², with ethanol as the food simulant) and PE film (50 µ, printed weight 6 g/m², with ethanol as the food simulant) showed no migration of substances above legal limits. Based on the results of these migration tests, we expect that the printed inks enable the final printed products to comply with the legal requirements for packaging for all kinds of foodstuff.

The manufacturer of the finished article and the filler have the legal responsibility to prove by appropriate migration testing that it is fit for its intended purpose.

In order to maintain low residual solvents concentration in the printed film, the printer must ensure sufficient drying of the inks, especially when retarders have been added. Residual solvent content must be regularly monitored.

The inks must not be used in the manufacture of packaging where the printed ink layer is intended to come into contact with foodstuff (direct food contact).

There are restrictions for the use of printing inks for applications where temperatures above 120 °C for extended periods of time are applied. For details, please see document "Food Packaging Inks for High Temperature Applications".

Health & Safety

The material safety data sheets contain all relevant information for the generation of appropriate internal plant instructions. The user is responsible for all local legislation requirements

Ink Handling

Please refer to General Guidelines for handling inks for flexible packaging

Contact addresses for advice and further information can be found under www.hubergroup.de

This Technical information sheet reflects the current state of our knowledge. It is designed to inform and advise. We assume no liability for correctness. Modifications may be made in the interest of technical improvement.