



CureInk UV – UB/UE 4200/4500

The UB/UE 4200 series of UV inks has been developed for sheet-fed offset, rotary label (letterpress) and continuous forms printing. The UB/UE 4500 series is specifically tailored to substrates that are susceptible to picking.

CureInk UV - UB/UE 4200/4500		Fastness properties per DIN 16 524/25				
Euroscale		Light WS	Alcohol	Solvent mixture	Alkali	UV varnish
Yellow	41 UB/UE 4200*	5	+	+	+	+
Magenta	42 UB/UE 4200*	5	+	+	-	+
Cyan	43 UB/UE 4200*	8	+	+	+	+
Black	49 UB/UE 4200*	8	+	+	+	+
Lightfast version						
Yellow	41 UB/UE 4001	7	+	+	+	+
Magenta	42 UB/UE 4001	7	+	+	+	+

WS = blue wool scale

* UB/UE 4500 is available with low tack formulation

* Coloristic according DIN ISO 2846-1

Special properties

- High colour intensity
- Wide range of fount tolerance
- Rapid adjustment of a stable ink/water balance
- Fast curing
- Minimal misting
- Suitable for laser printers (pre-production test is necessary)

Range of applications

The UB/UE 4200/4500 series are suitable for:

- coated and uncoated paper grades and card stocks
(highly absorbent stocks can greatly reduce the curing speed)
- thermal papers
(a number of thermal papers react to UV vehicles; for this reason, always carry out a test prior to beginning the print run)
- conditionally for pretreated PE, PP (corona or gas flame) or preprimed material*
- top-coated grades of board*

We recommend application of a UV varnish in order to provide effective protection of the print image. See [TI 32.09 E](#) entitled „CureLac UV for UV curing“.

* Non-absorbent substrates must have a surface tension of at least 38 mN/m in order to ensure optimum ink adhesion. In view of the large number of substrate suppliers and different substrates and substrate grades available, we recommend you carry out an adhesion test prior to beginning the print run.

Subsequent laser printing of UV-printed products

When using these inks in a laser printer, overprinting problems can arise, especially in image areas with very high ink coverage. We recommend that ink coverage of 50 % is not exceeded in such areas.

When the fusing temperatures of toners are high, there is a possibility of deposits building up on the fusing roller or fusing assembly of the hot-laser printer - even more so when the amount of ink and varnish being applied is high - due to thermoplastic properties of the cured ink or varnish films.

PANTONE® Rhodamine Red, Purple, Blue 072, Reflex Blue and HKS® 27, 33 and 43 also cause problems to the poor temperature resistance of their pigments as the toner is fused. They must be substituted by inks of a similar hue but with temperature-resistant pigments.

Food and confectionery packaging

More information on the subject of food and confectionery (semi-luxury foods and tobacco) packaging can be found in the information sheet entitled „Printing inks for food packaging“ published by the German Printing Ink Manufacturers' Association and in the [TI 32.08 E](#) entitled „UV inks and varnishes for food packaging“.

Printing auxiliaries

The inks are always supplied ready to use. The following auxiliaries are available to help you adjust the process inks in exceptional cases:

- **UV Paste Reducer 40 U 1002** (reduces tack)
- **Activator Paste 40 U 1003**

Classification

Safety Data Sheet available on request.

Shelf life

At least 12 months when stored under the correct conditions (20 °C, protected against heat and light)

How supplied

2,5-kg cans

Contact addresses for advice and further information can be found under www.hubergroup.de

This Technical information reflects the current state of our knowledge. It is designed to inform and advise. We assume no liability for correctness. Modifications may be made in the interest of technical improvement.